



CONQUEROR CONTOUR

PAPELES NO ESTUCADOS

Papel fabricado por ArjoWiggins

Terminación Contour (martillada)

Fibra más larga lo que le otorga al papel una mayor resistencia.

Garantizado para láser e Inkjet en gramajes bajos.

Papel con sello de agua en 100g.

Papel libre de ácido.

Papel libre de cloro elemental (ECF).

Papel 100% Fibra Virgen.

Conqueror tiene la siguiente certificación:
FSC (más información en GMS)

Recomendaciones de Impresión

Siegwerk Tempo Rapid

Armstrong UK SNT-N

Mitsuboshi Astro Super

Plisado debe realizarse paralelo al sentido de fibra del papel.

CONQUEROR es un papel ideal para impresión offset, aplicación de cuños, folias y troqueles entre otros.

El uso de fibras de algodón en la fabricación de un papel, le confieren un aspecto visual y táctil de gran calidez y un "sonido" muy particular.

Las fibras de algodón son más largas y resistentes, lo que contribuye a lograr un papel de mayor resistencia, por lo que es muy indicado para aplicación de cuños y plisados de alta exigencia.



CONQUEROR CONTOUR

PAPELES NO ESTUCADOS

Conqueror Contour

conqueror[†]

Common Attributes	Units	Test Method	100gsm	120gsm	160gsm	300gsm
Wood Pulp & Bleach Type			ECF Cotton Linters, FSC ECF Virgin Woodfree,			
Printing Process Suitability			Litho, Letterpress, Silk Screen, Dry Offset (Toray)			
Mono laser Guaranteed			<input checked="" type="checkbox"/>	Not guaranteed for office print technology		
Colour Laser Guaranteed			<input checked="" type="checkbox"/>			
Mono Ink Jet Guaranteed			<input checked="" type="checkbox"/>			
Colour Ink Jet Guaranteed			<input checked="" type="checkbox"/>			
Recommended p.H. of Fount Solution			5.5 ± 0.5			
Surface p.H.		TAPPI 5290M	≈ 7.5			
None Aging Credentials		ISO 9706	Yes			
Environmental Label		ISO 14001	Yes			
Quality Management		ISO 9002 : 2000	Yes			
Moisture Content	%	ISO 287	5,7		6,7	
Relative Humidity	%	TAPPI T502	35 – 55		40 - 60	

Caliper	µm	ISO 534	132*	156*	210*	430*
Whitest Shade Opacity	%	ISO 2471				
Bendtsen Roughness	ml/min	ISO 2494	Ω 800	Ω 800	Ω 800	Ω 1300
Stiffness M Direction C Direction	mN	ISO 2493 L+W, TABER				

* Due to the embossing process the thickness of the paper will vary so the caliper values are for guidance only.

Ω Conqueror Texture Contour is textured to a visual standard therefore it is not possible to give accurate roughness or stiffness values.

These specifications are the property of Arjo Wiggins Fine Papers Ltd and may be changed without prior notice. They are target values only for use as a guide.