

CLASSIFICATION OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1:2018

Classification no.	2024-Efectis-R000433
Sponsor	Antalis International 8, rue de Seine 92100 Boulogne-Billancourt FRANCE
Product name	Coala WallDesign NW 350g
Prepared by	Efectis Nederland BV
Notified body no.	1234
Author(s)	A. González Santamaría M.Sc. J.L. Onderwater B.Sc.
Project number	ENL-24-000411
Date of issue	May 2024
Number of pages	5

1. INTRODUCTION

1.1 PRODUCT NAME

This classification report defines the classification assigned to **Coala WallDesign NW 350g** in accordance with the procedures given in EN 13501-1:2018.

1.2 ASSESSMENT INFORMATION

The assessment of the editorial and technical alterations between the issues 2020 and the A1:2022 version of the test standard EN 13823. Date of issue: April 2024
Original date of issue: December 2022

Efectis compared the two versions of the EN 13823 standard and concluded that the result from the tests according to the EN 13823:2020 standard is still valid according to the EN 13823:2020+A1:2022 standard. Therefore this report can be used for classification according to EN 13501-1:2018.

2. DETAILS OF CLASSIFIED PRODUCT

2.1 GENERAL

The product, **Coala WallDesign NW 350g**, is defined as a wall covering.

2.2 IMPORTER

Antalis International
8, rue de Seine
92100 Boulogne-Billancourt
FRANCE

2.3 PRODUCT DESCRIPTION

According to the sponsor the product is composed of:

- Flame retardant vinyl topcoat with a mass per unit are of approx. 310 g/m²;
- Nonwoven backing with a mass per unit are of approx. 40 g/m²;
- Glued with adhesive Vescom 2000 with a mass per unit area of approx. 200 g/m².

The product has a total thickness of 0.4 mm and a mass per unit area of approx. 350 g/m².

3. STANDARDS, REPORTS, RESULTS AND CRITERIA IN SUPPORT OF THIS CLASSIFICATION

3.1 APPLICABLE (PRODUCT) STANDARDS

EN ISO 11925-2:2020	Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test
EN 13823:2020 / EN 13823:2020+A1:2022	Reaction to fire tests for building products - Building products, excluding floorings exposed to the thermal attack by a single burning item

EN 13238:2010	Reaction to fire tests for building products - Conditioning procedures and general rules for selection of substrates
EN 13501-1:2018	Fire classification of construction products and building elements Part 1: Classification using data from reaction to fire tests
EN 15102:2019	Decorative wall coverings – Roll and panel form products

3.2 REPORTS

Name of Laboratories	Name of sponsor	Report ref. no.	Test method
Efectis Nederland BV THE NETHERLANDS	Antalis International FRANCE	2021-Efectis-R001529 2021-Efectis-R001530	EN ISO 11925-2:2020 EN 13823:2020

3.3 TEST RESULTS

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – maximum	Compliance with parameters
EN ISO 11925-2				
Surface flame impingement	Fs ≤150 mm	6	35	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	45	-
	Ignition of filter paper		-	Compliant

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
	FIGRA _{0.2MJ} [W/s]	3	0.0	-
	FIGRA _{0.4MJ} [W/s]		0.0	-
	THR _{600s} [MJ]		0.4	-
	LFS < edge		-	Compliant
	SMOGRA [m ² /s ²]		0.0	-
	TSP _{600s} [m ²]		36.0	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

3.4 CLASSIFICATION CRITERIA

Fire classification of construction products and building elements Excluding floorings and linear pipe thermal insulation products			
Classification criteria			
Class Test method(s)	B	C	D
EN ISO 11925-2 Exposure = 30 s	F _s ≤ 150 mm within 60 s Ignition of the paper in EN ISO 11925-2 results in a d2 classification.		
EN 13823	FIGRA _{0.2 MJ} ≤ 120 W/s LFS < edge of specimen THR _{600s} ≤ 7.5 MJ	FIGRA _{0.4 MJ} ≤ 250 W/s LFS < edge of specimen THR _{600s} ≤ 15 MJ	FIGRA _{0.4 MJ} ≤ 750 W/s
Additional classification			
Smoke production	s1 = SMOGRA ≤ 30 m ² /s ² and TSP _{600s} ≤ 50 m ² ; s2 = SMOGRA ≤ 180 m ² /s ² and TSP _{600s} ≤ 200 m ² ; s3 = not s1 or s2		
Flaming Droplets/particles	d0 = no flaming droplets/ particles in EN 13823 within 600 s; d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s; d2 = not d0 or d1.		

4. CLASSIFICATION AND FIELD OF APPLICATION

4.1 REFERENCE OF CLASSIFICATION

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

4.2 CLASSIFICATION

The product, **Coala WallDesign NW 350g**, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

Reaction to fire classification: B – s1, d0

4.3 FIELD OF APPLICATION

This classification is valid for the following product parameters:

Thickness	0.4 mm
Surface density	350 g/m ²
Other properties	With print

This classification is valid for the following end use applications:

Substrate	Non-combustible (A1 or class A2 with a density $\geq 870 \pm 50$ kg/m ³ , according to EN 13238)
Application	Wallcovering
Air gap	Not applicable
Methods and means of fixing	Glued to the substrate according to the manufacturer's instructions using the special adhesive Vescom 2000
Joints	Vertical

4.4 DURATION OF THE VALIDITY OF THIS CLASSIFICATION REPORT

Consult classification standard and national laws and regulations for limitations on the period of validity of the classification.

5. LIMITATIONS

This classification document does not represent type approval or certification of the product.

The classification assigned to the product in this report is within the context of system 1 **Assessment and Verification of Consistency of Performance (AVCP)** and **CE marking** under the **Construction Products Regulation**. The sampling procedure has been performed in consultation with the certification authority.



A. González Santamaría M.Sc.
Project leader Reaction to Fire



J.L. Onderwater B.Sc.
Project leader Reaction to Fire