

MITSUBOSHI

PRINTING INK CO., LTD.



Since 1923

June 29, 2015.

To whom it may concern ;

TECHNICAL DATA SHEET

Product Name : MG-03 RM ROYAL GOLD MIDDLE

1) PHYSICAL DATA

		STD
1. Tack (Ink-o-meter) (32°C, 400 rpm, 1 Min.)		10.0±1.0
2. Flow (Spread-o-meter)(25°C, 1 Min) Reological Properties		41.0±1.0
3. Viscosity (Laray Viscometer)		35.0±10.0
4. L* a* b* Value (Chromo Meter CR 200 Minolta)	L*	50.57±1.00
	a*	6.28±1.00
	b*	26.34±1.00
5. Color Strength (Gretag Macbeth 196 Densitometer)	Y	0.99±0.05
	M	0.81±0.05
	C	0.66±0.05
	V	0.73±0.05
6. Light Fastness		5
7. Alkali Resistance		3

* Light Fastness & Alkali Resistance : (strong) 5 – 3 – 1 (week)

2) Type of Dryness : Oxidation & Penetration

..... E. & O. E.

MITSUBOSHI PRINTING INK CO.,LTD.

Manager of Foreign Dept.

HIGASHI, 1-103, FUNAO- CHO, HAMADERA NISHIKU SAKAI, OSAKA, 592-8341, JAPAN

Phone +81-72-261-8250 Fax +81-72-264-1421 E-Mail : tnatto@mitsuboshi-ink.co.jp